

**TAITA CHEMICAL CO LTD (TTC)**

12TH FL, B AREA, CHINA GENERAL PLASTICS BLDG, NEI HU DISTRICT 39 JI HU RD,  
TAIPEI 114 TW

**5000S****Acrylonitrile Butadiene Styrene (ABS), furnished as pellets**

Color	Min Thk (mm)	Flame Class	Flame		RTI		RTI Str
			HWI	HAI	Elec	Imp	
ALL	1.5	HB	4	4	60	60	60
	3.0	HB	4	4	60	60	60

Comparative Tracking Index  
(CTI): **1**

Dimensional Stability (%): -

High-Voltage Arc Tracking Rate  
(HVTR): **0**

High Volt, Low Current Arc Resis  
(D495): **6**

Dielectric Strength (kV/mm): **22**

Volume Resistivity (10<sup>x</sup> ohm-cm) : **22**

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents.

ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 1983-10-13

Last Revised: 2003-10-24 Underwriters Laboratories Inc®

**IEC and ISO Test Methods**

Test Name	Test Method	Units	Thickness	
			Tested (mm)	Value
Flammability	IEC 60695-11-10	Class (color)	1.5	HB75 (ALL)
			3.0	HB40 (ALL)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	C	-	-
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	C	-	-
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	-

IEC Ball Pressure	IEC 60695-10-2	C	-	-
ISO Heat Deflection (1.80 MPa)	ISO 75-2	C	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	$\text{kJ/m}^2$	-	-
ISO Izod Impact	ISO 180	$\text{kJ/m}^2$	-	-
ISO Charpy Impact	ISO 179-2	$\text{kJ/m}^2$	-	-

Underwriters Laboratories Inc®