


UL Certification

■ **Grade** : VE-1877

Component - Plastics					E115797		
CHEIL INDUSTRIES INC CHEMICALS DIV							
R & D CENTER, 332-2 GOCHUN-DONG, EUMWANG-SHI KYONGGI-DO 437-010 KR							
VE-1877+							
Polystyrene (PS), "STAREX", furnished as pellets							
Color	Min Thk (mm)	Flame Class	HWI	HAI	RTI Elec	RTI Imp	RTI Str
ALL	1.5	V-0	2	3	50	50	50
	2.1	V-0	2	3	50	50	50
	3.0	V-0	-	-	50	50	50
Comparative Tracking Index (CTI): 1				Dimensional Stability (%): -			
High-Voltage Arc Tracking Rate (HVTR): 2				High Volt, Low Current Arc Resis (D495): 7			
Dielectric Strength (kV/mm): -				Volume Resistivity (10 ^x ohm-cm): -			
UL94 small-scale test data does not pertain to building materials, furnishings and related contents. UL94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by ULI.							
Report Date: 1995-08-31							
Last Revised: 2008-02-15							
Underwriters Laboratories Inc®							

IEC and ISO Test Methods

Test Name	Test Method	Units	Thickness Tested (mm)	Value
IEC Flammability	IEC 60695-11-10	Class (color)	1.5	V-0 (ALL)
			2.1	V-0 (ALL)
			3.0	V-0 (ALL)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	C	-	-
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	C	-	-
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	-
IEC Ball Pressure	IEC 60695-10-2	C	-	-
ISO Heat Deflection (1.80 MPa)	ISO 75-2	C	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	kJ/m²	-	-
ISO Izod Impact	ISO 180	kJ/m²	-	-
ISO Charpy Impact	ISO 179-2	kJ/m²	-	-

Underwriters Laboratories Inc®