



INJECTION[H1500]

- **Attributes :** High Stiffness
- **Applications :** General Houseware
- **Certification :** -

- **Properties DATA SHEET**

Properties	Test Method	Unit	Properties
Melt Flow Rate 230_... 2.16kg	D-1238	g/10min	12.0
Density	D-1505	g/ㄗ	0.9
Mold Shrinkage	HPC Method	%	1.60
Tensile Strength at Break	D-638	kg/ㄗ	350
Ultimate Elongation	D-638	%	>100
Flexural Modulus of Elasticity	D-790	kg/ㄗ	15,000
Hardness	D-648	R	115
IZOD Impact Strength 23_...	D-256	kg.cm/cm	3.0
IZOD Impact Strength - 10_...	D-256	kg.cm/cm	-
DU-POINT Impact Strength 23_...	HPC Method	kg/ㄗ	
DU-POINT Impact Strength -10_...	HPC Method	kg/ㄗ	
Heat Resistance 130_...	Air Oven	Hour	<500
Heat Distotion 4.6kg/ㄗ	D-648	...	105
HAZE(2mm)	D-748	%	
Flamability		UL	HB

Above data are not the spec. of products, but only for reference.