Component - Plastics **E162823**

FORMOSA CHEMICALS & FIBRE CORP PLASTICS DIV

201 TUNG HWA N RD, TAIPEI 105 TW

K1011

Polypropylene (PP), "TAIRIPRO", furnished as pellets

Color	Min Thk (mm)	Flame Class	HWI	HAI	RTI Elec	RTI Imp	RTI Str
ALL	1.5	HB	2	3	65	65	65
	3.0	-	-	-	65	65	65

Comparative Tracking Index (CTI): **0**

Dimensional Stability (%): **-**

High-Voltage Arc Tracking Rate (HVTR): **0**

High Volt, Low Current Arc Resis (D495): **4**

Dielectric Strength (kV/mm): **-**

Volume Resistivity (10^x ohm-cm) : **-**

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date:2001-08-21
Last Revised:2006-10-31

Underwriters Laboratories Inc®

IEC and ISO Test Methods

Test Name	Test Method	Units	Thickness Tested (mm)	Value
Flammability	IEC 60695-11-10	Class (color)	1.5	HB75 (ALL)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	C	-	-
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	C	-	-
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	-
IEC Ball Pressure	IEC 60695-10-2	C	-	-
ISO Heat Deflection (1.80 MPa)	ISO 75-2	C	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	kJ/m^2	-	-
ISO Izod Impact	ISO 180	kJ/m^2	-	-
ISO Charpy Impact	ISO 179-2	kJ/m^2	-	-

Underwriters Laboratories Inc®